

VX Levelguard EP2860 TC is a water-based epoxy finish coat specifically developed for green concrete epoxy finish coating.

ADVANTAGES

- Low odor/VOC
- Low toxic
- Excellent adhesion
- Excellent gloss and gloss retention
- Excellent stain resistance
- Excellent hardness development

APPLICATION

- Floor coating top coat
- Industrial maintenance
- Industrial medicine
- Industrial food

TYPICAL PROPERTIES

Color	Depend on purchase / RAL Std colour
Gloss level	Gloss
Volume solid	98%
Dry film thickness	Min 300 microns - 1000 microns
Theoretical coverage	1 - 3 M ²
Mixing ratio by weight	Base : Hardener = 5 : 1
Diluent	Water
Gel Time / Pot Life	45 minutes
Hardness	81 (Shore - D)
Flash point	Up to 80°C
Drying Time:	
Touch Dry	2 hours
Hard Dry	8 hours

Disclaimer. The information and the recommendations relating to the application and end use of this product are given in good faith and are based on the information provided by the manufacturer of the product and/or the Company's current knowledge and experience in connection with the product when properly stored, handled and applied under normal conditions and no liability of final function at the job site is assumed. In practice, the differences in materials substrates and actual size conditions are such that no warranty in respect of merchantability of or fitness for particular purpose, nor any liability by the Company will be accepted for misuse, misreading or derivation from recommended guidelines in respect of this product and the user shall determine the suitability of the product for his intended use and all risks and liability in connection therewith. The information contained in the brochure may change at any time without notice.



PACKAGING

5 liter-set, 20 liter-set

SHELF LIFE

2 Years

APPLICATION

Application Methods :

Brush, Roller or Airless Spray Recommended

Humidity

RH 85% Max

SAFETY PRECAUTION

Keep away from heat, spark and open flames. Avoid breathing of vapour on skin and eye contact. Keep container closed and store in cool, ventilated area when not in use. Proper ventilation and protective measures must be provided during mixing, application and drying, to keep vapour concentration within safe limits and to protect against toxic hazard.

Necessary safety equipment must be used and ventilation requirements carefully observed, especially in confined or enclosed spaces, such as tank interior and building

